

Alcantara® 0.6mm

MAIN CHARACTERISTICS			
COMPOSITION	ALCANTARA®	POLYESTER POLYURETHANE	73 ± 3 % 27 ± 3 %
THICKNESS			0.57 ± 0.10 mm
UNIT WEIGHT		UNI EN 29073-1	160 ± 25 g/m ²
WIDTH			≥ 142 cm
DIMENSIONAL STABILITY (WATER 40°C)		UNI EN ISO 25077 + 6330	≤ 3 %
BREAKING LOAD	LENGTHWISE CROSSWISE	UNI EN 29073-3	≥ 120 N/5cm ≥ 60 N/5cm
TEAR STRENGTH	LENGTHWISE CROSSWISE	EN ISO 13937-1	≥ 6 N ≥ 3 N
MARTINDALE ABRASION 12 kPa		EN ISO 12947-4	(*) 2000 cycles
COLOR FASTNESS (**)			
TO LIGHT	Xenotest Beta 36h	UNI EN ISO 105 B02	≥ 5.5 blue scale (1-8)
TO DOMESTIC WASHING	Tone change Staining	EN ISO 105 C06	≥ 4 grey scale (1-5) ≥ 3 white scale (1-5)
TO DRY CLEANING	Tone change Staining	AATCC 132	≥ 4 grey scale (1-5) ≥ 3 white scale (1-5)
TO RUBBING	Dry Wet	EN ISO 105 X12	≥ 4 white scale (1-5) ≥ 3 white scale (1-5)
TO PERSPIRATION	Acid - Basic	EN ISO 105 E04	≥ 4.5 white scale (1-5)
(*) Slight change in the appearance of product surface. (**) Slight shade variations from one production batch to another one are possible on these products.			
GENERAL WASHING			